




# **IGLU'** H 6 cm





Ventilated under-floor cavities for civil and industrial buildings that are being built new or reconstructed. - Urban infrastructure structures: squares, sidewalks, sports facility.

- Creation of an intermediate slab or roofing for cavities used for ventilation and the passage of systems.
- Rooms used for humidity and temperature control: drying cells, cold rooms, greenhouses, storage rooms and cellars.
- Underground pipes for the passage of utilities. Inspectionable cavities and pits.
- By filling it in simply with expanded clay, it can be used to create roof-top gardens.
- Underground ducts for the dispersion of water and for drainage.
- Overhead sidewalks for passenger loading and unloading or the creation of floating floors.
- · Levelling height.

# Made of ALAPLEN® CP30







Passage of nr. 4 tubes Ø 35 mm for tunnel

The images are only for examples. Recyclable material is allowed a size tolerance of  $\pm$  1,5%.



0,007m<sup>3</sup>/m<sup>2</sup>

## Quantity (of concrete to the crown)

The volume may vary depending on the pouring condition and the tolerance of the material.

rev. 20-03/2023 Pag. 1/3

Loads <sup>[1]</sup> kN/m²	Slab cm	Mesh Ø mm Meshcm x cm	Thickness of the lean concrete cm	Pressure at pillar base <sup>[2]</sup> MPa
15	4	Ø 5/ 25 x 25	5 7 10	0,110 0,074 0,046
50	5	Ø 5/ 20 x 20	7 10 15	0,224 0,137 0,074
100	8	Ø 6/ 20 x 20	10 15 20	0,270 0,144 0,089

<sup>[1]</sup> Characteristic values


The table expresses, starting from the various examples of overload and of thickness (to be given to the slab), the pressures that would be applied to the feet of the structure, in relation to the (eventual) thicknesses of the lean concrete. The overload hypotheses are indicated in table as an example; the actual load capacity is far superior.

To know the exact values or sizing as shown in the project, contact the technical department.

The Technical Office is available to provide planning support both in the preliminary and in the executive phase to determine the technical characteristics of the structures, the related construction costs and perform comparative analyzes with alternative technical solutions. Upon request, it is also possible to take advantage of technical assistance on site.

#### **TECHNICAL DATA**


# Iglu'® H 6



Useful size*	cm	50 x 50
Height* H	cm	6
Quantity of concrete to the crown**	$m^3/m^2$	0,007
Average piece weight	kg	0,757
Pallet dimensions	cm	110 x 110 x 253
M² pallet	m²/PAL	150
Pieces per pallet***	pz/PAL	600
Pallet weight***	kg/PAL	467

<sup>\*</sup> Recyclable material is allowed a size tolerance of  $\pm$  1,5%.

## **DRY ASSEMBLY METHOD**



To ensure a correct installation and perfectly created under-floor cavity please refer to the product's usage requirements.

Dry-stone time-exposure: 80 m²/h

rev. 20-03/2023 Pag. 2/3

<sup>[2]</sup> Project values (Ultimate SLU Limit State - Coefficients A1)


<sup>\*\*</sup> The volume may vary depending on the pouring condition and the tolerance of the material.
\*\*\* For production necessity the technical data can be change.

#### **TECHNICAL PACKING AND TRUCKING**



1 pallet: 4 piles of 150 pieces


Pieces per pallet: 600



(a x b x h)

110 x 110 x 253

measurements are in cm



#### **LABELLING**

## Each pallet is identified with:



A coloured band containing: the brand, a type image of the product, the Company name, teh website and any warnings.



A lebel with the following informations: product's name and code, quantity, Certificate of the Environmental Compatibility, date of production, shift of production, n° of the worker, production line batch.

# **CREDITS**

- BBA;
- Declaration of Performance Conformity;
- Hygienic certificate;
- Acoustic check for verification of DIN standards; Avis Technique;
- Rupture load tests;
- Productive process monitoring tests;
- Certificate of Environmental Compatibility.

The product does not fear the weather and can be stored outside. Take the utmost care to prevent the product from being deformed or overstressed during the unloading, storage and assembly. In case of disposal the product is totally recyclable.



Tel. +39 0422 2083 - Fax +39 0422 800234 export@daliform.com - www.daliform.com Via Postumia Centro, 49 - 31040 Gorgo al Monticano (TV) - Italy











Certified Management System UNI EN ISO 90

rev. 20-03/2023 Pag. **3** /3